Research Square

Preprints are preliminary reports that have not undergone peer review.
They should not be considered conclusive, used to inform clinical practice,
or referenced by the media as validated information.

Advances in Drying Technology for Transformer Insulation: A Comprehensive Overview

Mohd. Tareq Siddiqui

mohd.tareq.siddiqui@gmail.com

Principal Aurangabad College of Engineering

Research Article

Keywords: Transformers, Insulation Drying, Vapor Phase Drying, Cellulose Insulation

Posted Date: October 29th, 2025

DOI: https://doi.org/10.21203/rs.3.rs-7505870/v1

License: This work is licensed under a Creative Commons Attribution 4.0 International License.
Read Full License

Additional Declarations: No competing interests reported.

Abstract

The rising global demand for electricity and the increasing complexity of power distribution systems underscore the need for advanced manufacturing processes in transformer production, especially for insulation drying. Vapor Phase Drying (VPD) has emerged as a game-changing technique that significantly enhances the drying efficiency of cellulose-based insulation materials in power transformers. Unlike conventional approaches, VPD utilizes solvent vapors for consistent heating, cutting drying times by up to 18% without compromising insulation quality. Experimental studies demonstrate noteworthy improvements in metrics such as the polarization index (PI) and dielectric absorption ratio (DAR), reaffirming the potential of VPD to boost transformer lifespan and operational reliability. This paper reviews the principles, advantages, and practical applications of VPD technology, offering valuable insights for the future of transformer manufacturing.

1. Introduction

Transformers are fundamental to modern power distribution, enabling efficient energy transfer over long distances. With growing energy demands and the integration of renewable energy into power grids, transformers must meet increasingly stringent performance requirements. A key factor determining transformer reliability and longevity is the condition of its insulation system [2, 3].

Cellulose-based materials, such as Kraft paper and pressboards, are widely used for transformer insulation due to their superior dielectric properties and mechanical strength [5]. However, these materials are highly hygroscopic, readily absorbing moisture from their environment [6]. Moisture in insulation not only accelerates the aging process but also diminishes its dielectric strength, increasing the risk of operational failures [6, 7].

Traditional drying methods, including hot air drying, vacuum drying, and oil circulation, have been employed to address moisture-related issues. However, these methods often fall short due to inefficiencies such as prolonged drying cycles, inconsistent moisture removal, and high energy consumption. These challenges necessitate the development of advanced drying technologies that deliver better results in less time.

Vapor Phase Drying (VPD) represents a breakthrough in transformer insulation drying. By leveraging solvent vapors for uniform heating, VPD addresses the limitations of conventional methods, offering faster drying times, enhanced energy efficiency, and superior insulation quality [2]. This paper provides a detailed review of VPD technology, exploring its principles, benefits, and practical applications, supported by experimental validation to showcase its transformative potential for the transformer industry.

2. Importance of Moisture Management in Transformer Insulation

Transformer reliability heavily depends on maintaining optimal insulation conditions [6]. Cellulose-based materials, widely used for transformer insulation, are known for their excellent dielectric and mechanical properties. However, their hygroscopic nature makes them highly prone to absorbing moisture during storage, handling, or operation. The presence of moisture in insulation leads to severe performance degradation and poses significant operational risks [7].

2.1 Impact on Dielectric Strength

Moisture adversely affects the dielectric properties of cellulose insulation, drastically lowering its breakdown voltage. Even minor increases in moisture content can have exponential impacts on dielectric strength, making the transformer vulnerable to failure under high voltage stress. For instance, insulation with 1.5% moisture content has been shown to exhibit far weaker dielectric properties than insulation with 0.3% moisture [6, 7, 8].

2.2 Accelerated Aging of Insulation

The presence of moisture accelerates the aging process of cellulose through hydrolytic degradation [6, 8, 9]. This degradation weakens the insulation's mechanical structure, reducing its long-term reliability. Transformers operating in high-stress conditions are particularly susceptible to this accelerated aging, resulting in shortened lifespans [6, 8, 9].

2.3 Risk of Catastrophic Failures

Moisture increases the likelihood of partial discharges and other fault mechanisms [8]. Localized heating caused by the presence of moisture can lead to the formation of gas bubbles within the insulation, which act as hotspots for electrical discharges. Over time, these discharges can escalate into complete dielectric breakdown, resulting in transformer failures that are often catastrophic and costly.

2.4 Insulation Health Metrics

Critical metrics, such as the Polarization Index (PI) and Dielectric Absorption Ratio (DAR), are heavily influenced by moisture levels [7]. Higher moisture content results in suboptimal values for these metrics, indicating compromised insulation health. This necessitates immediate attention to moisture removal, particularly during the manufacturing process.

Effective management of moisture in transformer insulation is critical to ensure long-term operational reliability. Advanced drying techniques like Vapor Phase Drying (VPD) provide a robust solution to this challenge, offering superior moisture removal while preserving the integrity of the insulation material [2].

3. Overview of Traditional Drying Techniques

Transformer insulation drying has historically relied on well-established methods such as hot air drying, vacuum drying, and oil circulation. While these techniques have been integral to transformer

manufacturing, their limitations in terms of efficiency and consistency have paved the way for more advanced approaches.

3.1 Hot Air Drying

Hot air drying involves circulating heated air over the insulation to evaporate moisture. While simple and widely adopted, this method has several drawbacks [4]:

- **Inconsistent Drying**: Non-uniform air circulation often leads to uneven heating, leaving pockets of insulation with residual moisture.
- **Oxidation Risk**: Extended exposure to hot air can oxidize the cellulose material, compromising its dielectric properties.
- **Prolonged Drying Cycles**: Due to the low thermal conductivity of cellulose, the process requires extended drying times, making it inefficient for large-scale manufacturing.

3.2 Vacuum Drying

Vacuum drying creates a low-pressure environment, reducing the boiling point of water and enabling moisture removal at lower temperatures. This method offers some advantages but is hindered by [4]:

- **Lengthy Cycle Times**: Moisture removal from thick insulation layers or large transformers often takes several days.
- **Energy Demand**: Maintaining a vacuum chamber and simultaneously heating the transformer consumes significant energy, reducing overall efficiency.

3.3 Oil Circulation

In oil circulation, heated transformer oil is circulated through the insulation, absorbing moisture that is then filtered out. This technique is often used for maintenance and repairs but is less effective for initial manufacturing due to [4]:

- **Slow Moisture Removal**: The process is time-intensive and not ideal for meeting production schedules.
- **High Energy Consumption**: Heating and continuously circulating the oil require substantial energy resources.

These limitations highlight the need for advanced drying methods that address inefficiencies while preserving insulation integrity. Vapor Phase Drying (VPD) emerges as a superior alternative, offering faster drying times, uniform moisture removal, and enhanced energy efficiency.

4. Principles of Vapor Phase Drying Technology

Vapor Phase Drying (VPD) is a cutting-edge technique that employs solvent vapors to ensure consistent heating and efficient moisture removal from transformer insulation. The process relies on well-established thermodynamic principles and is executed in distinct stages to maximize drying efficiency [1].

4.1 Preparation Phase

The transformer is placed in a sealed vacuum chamber, and the surrounding air is evacuated to create a low-pressure environment. A solvent, typically kerosene, is heated to approximately 130°C to generate vapor. This preparation ensures optimal conditions for the drying process [1].

4.2 Heating and Drying Phase

The solvent vapors are introduced into the chamber, condensing on the surface of the insulation. The condensation process releases latent heat, which uniformly raises the insulation's temperature and evaporates moisture. This stage ensures consistent drying throughout all insulation layers, including those that are typically hard to reach [1].

4.3 Pressure Reduction Phase

The vacuum level in the chamber is increased, further lowering the boiling point of water. This facilitates the evaporation of any remaining moisture trapped deep within the insulation [1].

4.4 Fine Vacuum Stage

In the final stage, the vacuum is increased to a high level (approximately 0.1 torr), enabling complete removal of residual moisture. This ensures that the insulation achieves the desired moisture content, typically between 0.5% and 1.0% by weight [1].

The VPD process stands out due to its efficiency, reducing drying times by up to 20% compared to traditional methods, while ensuring uniform moisture removal and preserving the mechanical and dielectric properties of the insulation material [4].

5. Experimental Validation of VPD

To evaluate the efficiency and advantages of Vapor Phase Drying (VPD), experimental studies were conducted on 11 kV 5kva transformers having 12kg cellulose insulation at Chaitanya Electromagnets, Waluj MIDC, Aurangabad, Maharashtra, India. The trials focused on drying time reduction, insulation quality, and energy efficiency compared to the conventional method of vacuum drying.

5.1 Experimental Setup

For the fabrication of a vapor phase drying (VPD) set up for 11kv transformers as a model at Chaitanya Electromagnets (CEM), reference is taken from the vapor phase drying plant used for power

transformers at Vishwas Power Engineering Services (VPES), Nagpur. The vacuum oven at VPES is 12m x 9m x 9m in dimension and the average dimension of the core of power transformer with insulation is 7m x 4m x 3m. The ratio of volume of the vacuum oven and the core of power transformer with insulation is taken and found to be 11.57. This volume is the space remaining in the vacuum oven after the core of power transformer is loaded. For manufacturing the vapor phase drying (VPD) set up for 11kv transformers as a model at Chaitanya Electromagnets (CEM), the proportion of volume remaining in the vacuum oven after the core of transformer with insulation is loaded is taken as a reference point. At Chaitanya Electromagnets (CEM) the dimension of 11kv/400v 5kva transformers having 12kg cellulose insulation is 0.49m x 0.2m x 0.2m. Considering the proportion of volume, the vacuum oven having dimension 1m x 0.5m x 0.5m is made as per the requirements of Chaitanya Electromagnets (CEM). Also, the insulation material used for 11kv transformers is same as that is used in the power transformers [2].

5.2 Experimentation

Two identical transformers named transformer 1, and transformer 2, required for experimentation were supplied by CEM. Initially, one transformer of 11kv/400v 5kva having 12kg cellulose insulation (transformer 1) was processed through vacuum drying and readings were obtained with respect to the insulation layers temperature and moisture removed. The drying cycle was stopped when the moisture removal rate became stable. It was found that the drying cycle time required was 340 minutes as at this time, the moisture removal rate becomes constant indicating that the required moisture from the job has already been removed and further constant discharge of moisture is because of the leak rate which is present in any vacuum vessel [2]. Also, the end of drying cycle here is accepted as the values for insulation resistance and tan δ achieved are as per the standards [2, 10].

The other identical transformer (transformer 2) of 11kv/400v 5kva having 12kg cellulose insulation was processed through vapor phase drying. Readings were obtained with respect to the insulation layers temperature and moisture removal rate. The drying cycle was stopped when the level of measured moisture removal became same as that obtained for transformer 1. The end of drying cycle here is accepted as the values for insulation resistance and tan δ achieved are as per the standards [2, 10].

5.3 Drying Cycle Comparison

The drying performance was compared between traditional vacuum drying and VPD:

- **Vacuum Drying**: Achieved the target moisture content 340 minutes.
- **VPD**: Achieved the same moisture level in 280 minutes, reflecting a 18% improvement in drying time.

5.4 Insulation Quality Evaluation

Post-drying, the insulation quality was assessed using standard metrics:

- Polarization Index (PI): VPD-treated transformers exhibited PI values exceeding 2.0, indicating superior insulation reliability [10].

- Dielectric Absorption Ratio (DAR): VPD samples demonstrated marked improvements, confirming reduced moisture levels and enhanced performance [10].

5.5 Energy Efficiency

Energy consumption during the drying process was measured. VPD demonstrated a 15% reduction in energy use compared to vacuum drying, owing to its faster drying cycle and efficient heat transfer.

5.6 Observations and Conclusions

The experiments confirmed that VPD not only shortens drying times but also enhances insulation quality. These findings establish VPD as an effective and reliable drying method for large-scale transformer manufacturing.

6. Discussion and Industrial Applications

The implementation of Vapor Phase Drying (VPD) in transformer manufacturing marks a significant shift toward efficiency and reliability. The technology addresses persistent challenges in traditional drying methods and sets new benchmarks for insulation quality and operational cost-effectiveness.

6.1 Key Advantages of VPD

VPD offers several distinct advantages over conventional drying methods:

- **Uniform Heating**: By utilizing solvent vapors, VPD ensures consistent heat distribution across all layers of insulation, eliminating localized overheating and under-drying [4].
- **Accelerated Drying Cycles**: VPD reduces drying times by 12–15%, a significant improvement that enhances production efficiency, particularly in high-demand scenarios [4].
- **Energy Efficiency**: The process is inherently more energy-efficient, with reduced operational time and lower energy demands compared to methods like vacuum drying.
- **Enhanced Insulation Quality**: Metrics such as polarization index (PI) and dielectric absorption ratio (DAR) highlight the superior performance of VPD-treated insulation, which exhibits reduced moisture content and improved dielectric properties.

6.2 Industrial Applications

VPD’s adaptability makes it a suitable choice for various industrial scenarios, including:

- **Large Power Transformers**: The technology is particularly effective for high-voltage transformers, where insulation structures are large and complex [2]. Uniform drying ensures that these transformers meet stringent operational standards.
- **Specialized Transformer Designs**: VPD’s precision and control allow it to accommodate unique configurations, making it ideal for custom transformer manufacturing.

- **Maintenance and Retrofitting**: VPD can also be applied during transformer maintenance, where it efficiently removes moisture from aging or previously operational insulation.

6.3 Emerging Trends and Innovations

The future of VPD lies in hybrid drying systems and environmentally sustainable practices. For instance:

- **Integration with Hybrid Techniques**: Combining VPD with oil circulation or advanced vacuum methods could further enhance drying efficiency and adapt the process to transformers of varying sizes [2].
- **Green Solvent Alternatives**: Research into eco-friendly solvents could reduce the environmental footprint of VPD while maintaining its efficiency.
- **Automated Monitoring Systems**: Integrating IoT-based sensors and AI-driven optimization models can enable real-time control and predictive adjustments, ensuring peak performance for each drying cycle.

6.4 Challenges and Mitigation Strategies

While VPD offers substantial benefits, certain challenges must be addressed to maximize its potential:

- **High Initial Costs**: The infrastructure required for VPD, including vacuum chambers and solvent handling systems, represents a significant capital investment. However, the long-term savings in operational costs and enhanced product quality offset this expense [2].
- **Solvent Management**: The handling, storage, and disposal of solvents require strict adherence to safety and environmental regulations. Implementing closed-loop systems for solvent recycling can mitigate these concerns effectively.

By addressing these challenges, VPD can become the standard drying method in transformer manufacturing, paving the way for greater efficiency and sustainability.

7. Conclusion and Future Directions

Vapor Phase Drying (VPD) represents a transformative advancement in transformer insulation drying, combining efficiency, reliability, and superior insulation quality. This technology addresses the limitations of traditional methods, offering faster drying cycles, improved energy efficiency, and better insulation performance.

7.1 Summary of Findings

Vapor Phase Drying (VPD) has proven to be a transformative technology in the realm of transformer insulation drying. Its ability to overcome the limitations of traditional methods makes it a cornerstone for modern manufacturing processes. Key takeaways include:

- Drying Efficiency: VPD reduces drying times by up to 18%, streamlining production workflows and increasing throughput.
- Superior Insulation Quality: Metrics such as the polarization index (PI) and dielectric absorption ratio (DAR) validate the enhanced performance of insulation dried using VPD.
- Energy Savings: The process achieves significant reductions in energy consumption, contributing to cost savings and environmental sustainability.

7.2 Recommendations for Future Research

While VPD has established itself as a leading technology, further advancements can unlock its full potential:

- Scalability for Ultra-High-Voltage Transformers: Adapting VPD for even larger transformers requires innovations in equipment design and solvent handling.
- Environmental Innovations: Developing biodegradable or lower-impact solvents and closed-loop solvent recycling systems can improve the technology's environmental profile.
- Real-Time Process Optimization: Incorporating AI and IoT systems can provide real-time insights into drying performance, allowing for dynamic adjustments that improve efficiency and product quality.

7.3 Broader Implications

The widespread adoption of VPD could reshape the transformer manufacturing industry. Its energy-efficient processes and enhanced drying outcomes align with global trends toward sustainability and reliability in power systems. Moreover, by ensuring the long-term durability and reliability of transformers, VPD contributes to the broader goals of stable and resilient power distribution networks.

In conclusion, Vapor Phase Drying is not only an advanced drying method but a transformative tool for modernizing transformer production. With continued research and investment, its potential can be fully realized, ensuring that the power systems of tomorrow are robust, reliable, and environmentally sustainable.

Declarations

Acknowledgments

Chaitanya Electromagnets, D1/1, MIDC Waluj, Maharashtra, India, 431001. An ISO 9001:2008 certified company.

Partial financial support was received in the form of transformers (that were used for the experimentation) from Chaitanya Electromagnets, D1/1, MIDC Waluj, Maharashtra, India, 431001. An ISO 9001:2008 certified company.

References

1. Bharat Heavy Electricals Limited. (2003). "Transformers". Tata McGraw Hill, 2nd Edition, Page 275-290.
2. Dr. Mohd Tareq Siddiqui (2024). “Cycle time reduction using intermittent DC internal heating in vapour phase drying of cellulose-based insulation used in transformers”. Australian Journal of Electrical and Electronics ENGINEERING, https://doi.org/10.1080/1448837X.2024.2411472
3. Mats Dahlund, Paul Koestinger, Per Meyer. (2010). "Life Extension Of Power Transformers Oil Regeneration, On Site Drying And Onsite Repair". In Proceedings of the PdMSA 2010 Conference.
4. Mohd. Tareq Siddiqui, Dr. Jayant T. Pattiwar and Avinash P. Paranjape. (2017, April). "Vapor Phase Drying for Moisture Removal from Transformer Coil Insulation". International Journal of Scientific & Engineering Research, Volume 8, Issue 4, Page 20–24.
5. Paul Koestinger, Erik Aronsen, Pierre Boss, Günter Rindlisbacher. (2004). "Practical Experience With The Drying Of Power Transformers In The Field, Applying The Lfh** Technology". Paris: CIGRE.
6. Ajay Bangar, Rajan Sharma, H.P.Tripathi & Anand Bhanpurkar. (2012). "Comparative Analysis of Moisture Removing Processes from Transformer which are Used to Increase its Efficiency". Global Journal of Researches in Engineering Mechanical and Mechanics Engineering, Volume 12(Issue 5).
7. Diego F. García, Belén García, Juan Carlos Burgos. (2012, January). "Analysis of the influence of low-frequency heating on transformer drying – Part 1: Theoretical analysis". Electrical Power and Energy Systems, 84–89.
8. Rich Simonelli. (2013). "Water in Transformers". SPX Transformer Solutions.
9. Stephan Zabeschek and helmut Strzala. (2007, October). "Drying of High Voltage Power Transformers in The Field with a Mobile Vapour Phase Drying Equipment". Hedrich Vacuum Systems.
10. ANSI/NETA ATS-2009; American National Standard; Standard for Acceptance Testing Specifications for Electrical Power Equipment and Systems.

Figures



Figure 1

Experimental Set Up